

BEACON ADHESIVES CO.

125 MacQuesten Parkway S. • Mount Vernon, NY 10550 USA
Phone 914.699.3400 • Fax 914.699.2783
david@beaconadhesives.com
www.beaconadhesives.com

MagnaTac F-310

High temp. & chemical resistant thermoset epoxy

Viscosity	Color	Base	Wgt/Gal	Solids	Shelf Life
3000 cps	Amber	Ероху	9.1 lbs	100%	3 months
	Translucent				

MagnaTac F-310 is a one part, heat cure adhesive designed for high temperature applications including motor laminates, transform cores. **MagnaTac F-310** is formulated with exceptionally low hydrolysable chloride for exceptional chemical resistance to aggressive solvents and concentrated acids.

Curing information.

After MagnaTac F-310 been applied, parts are to be cured in accordance with the following schedule.

Temperature	Minimum Gel Time	Minimum cure time	Maximum Cure Time	
266F or 130 C	40 Min.	14 Hours	none	
284F or 140C	32 Min	7 Hours	none	
302F or 150C	20 min	4 hours	none	
320F or 160C	15 min	2 hours	none	
338F or 170C	10 min	1.5 hours	none	
356F or 180C	8 min	1 hour	none	
374F or 190C	6 min	45 min	none	
392F or 200C	4 min	30 min	24 hours	
428F or 220C	2 min	10 min	60 min.	



BEACON ADHESIVES CO.

125 MacQuesten Parkway S. • Mount Vernon, NY 10550 USA
Phone 914.699.3400 • Fax 914.699.2783
david@beaconadhesives.com
www.beaconadhesives.com

Page 2

Physcial Properties:

Once cured MagnaTac F-310 exhibits lap shear strength of 4500 PSI as per ASTM D1002.

Contacting Beacon Adhesives Co. Inc.

<u>Technical assistance</u>. Additional technical assistance is available by telephone and email.

Technical assistance telephone 914-699-3400

Technical email assistance: david@beaconadhesives.com

General information

Telephone 914-699-3400

Email: Louise@beaconadhesives.com

REACH and RoSH compliance:

We certify that all adhesive manufactured by Beacon Adhesives Co. Inc. are in compliance with both REACH and RoSH.